No Skidding®

266 Wildcat Rd, Toronto, ON M3J 2N5 Canada
Phone: (416) 667-1788 Fax: (416) 667-1783
sales@noskidding.com www.noskidding.com
or call us Toll Free at 1-800-375-0571
We warehouse within the U.S. for our U.S. customers

ALKYD
Slip Resistant Floor Coating
POLYURETHANE FORTIFIED
for general use indoors & outdoors

56101

Alkyd Slip Resistant Floor Coating - 56101

A polyurethane fortified alkyd high gloss finish for exterior and interior use, with excellent durability, gloss and colour retention containing phenolics and polyurethane resins. The product has easy application and good hiding power. Dries to a mar and print resistant highly washable and slip resistant finish. Contains tempered safety granules.

Intended Uses

A slip-resistant coating to protect interior and exterior floors of wood, metal or masonry. (Primer may be required depending on substrates - See below.)

Surface Preparations

Cement Floors (Raw): Apply two coats of product directly.

Previously Painted Surfaces: Surface must be clean dry, sound and free from loose paint etc. Remove grease and wax by washing with mineral spirits. Glossy surfaces should be dulled by sanding. For priming apply Alkyd undercoat where surface is porous.

Metal: Remove all loose rust and mill scale by wire brush, sand blasting or wheel abrading, as required. Make sure surface is clean from grease etc. Use red or white metal primer.

New Wood: Seal knots and problem surfaces with wood and knot sealer before painting. Shellac or Stain Blocker recommended. Use Alkyd undercoat or latex primer.

Masonry Surfaces: (Plaster, Cement, Concrete, etc.) All surfaces must be allowed to cure fully before painting. Smooth concrete floors should be roughened. Remove all loose chalk etc. from old masonry surfaces before painting. Use Latex primer for priming surface.

Product Specifications

Lustre: High Gloss

Application: Brush or Roll

Spreading Rate: 400-425 sq. ft./gal. 9.2 - 10.5 m2/L On non-porous surface

Dry Time: To Touch 6-8 hrs., Recoatable 16-24 hrs.

Specific Gravity: 1.20 ± .10

Viscosity: 74 - 90 KU

% Non Volatile: 65 min. (By Wt.)

Gloss: 80 min. (60 degrees HD)

Dry Film Thickness: 1.5 - 2 mils per coat

Flexibility: Passes 1/2" Mandrel

Other Data: If necessary to reduce for spray application, up to 10% mineral spirits may be used.

Colors: Medium Gray

PLEASE READ AND FULLY UNDERSTAND LABEL AND MSDS BEFORE USING.

Important: Seller's and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for the intended use, and the user assumes all risk and liability whatsoever in connection therewith. No statement of recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of the seller and manufacturer. Buyer assumes all risk and liability associated with disposal.

No Skidding® products are in use around the world in hotels, warehouses, factories, shopping malls, public transit systems, airports, hospitals and senior care, office complexes, restaurants, day care, schools, fitness clubs, government and military facilities.

The most complete range of slip injury prevention products in the World.

No Skidding®

www.noskidding.com

266 Wildcat Rd, Toronto, ON M3J 2N5 Canada
Phone: (416) 667-1788 Fax: (416) 667-1783
sales@noskidding.com www.noskidding.com
or call us Toll Free at 1-800-375-0571
We warehouse within the U.S. for our U.S. customers

* No Skidding® is a registered trademark of No Skidding Products, Inc., Toronto Canada

E.&.O.E.